

**Product Number: L15161**

**Product: Montmorillonite KSF**

Appearance	Pale gray to cream powder
Surface Area (m <sup>2</sup> /g)	20-40
Pore volume (ml/g at nm range by CCl <sub>4</sub> )	0.023 at 0 – 80
Pore volume (ml/g at nm range by Hg porosimeter)	0.19 at 15000 – 1750 0.05 at 1750 – 80 0.04 at 80 – 14 0.04 at 14 – 7.5
Loss of ignition (%)	7
Bulk density (g / l)	800 - 850

[www.alfa.com](http://www.alfa.com)

**NORTH AMERICA**  
Tel: +1-800-343-0660 or  
+1-978-521-6300  
Fax: +1-800-322-4757  
Email: [info@alfa.com](mailto:info@alfa.com)

**GERMANY**  
Tel: 00800 4566 4566 or  
+49 721 84007 280  
Fax: 00800 4577 4577 or  
+49 721 84007 300  
Email: [Eurosales@alfa.com](mailto:Eurosales@alfa.com)

**UNITED KINGDOM**  
Tel: 0800-801812 or  
+44 (0)1524-850506  
Fax: +44 (0)1524-850608  
Email: [UKsales@alfa.com](mailto:UKsales@alfa.com)

**FRANCE**  
Tel: 0800 03 51 47 or  
+33 (0)3 8862 2690  
Fax: 0800 10 20 67 or  
+33 (0)3 8862 6864  
Email: [frventes@alfa.com](mailto:frventes@alfa.com)

**INDIA**  
Tel: +91 8008 812424 or  
+91 8008 812525 or  
+91 8008 812626  
Fax: +91 8418 260060  
Email: [India@alfa.com](mailto:India@alfa.com)

**CHINA**  
Tel: +86 (010) 8567-8600  
Fax: +86 (010) 8567-8601  
Email: [saleschina@alfa-asia.com](mailto:saleschina@alfa-asia.com)

**KOREA**  
Tel: +82-2-3140-6000  
Fax: +82-2-3140-6002  
Email: [saleskorea@alfa-asia.com](mailto:saleskorea@alfa-asia.com)